



ARACO PRIME SB

Solvent Based High Performance Epoxy Primer

Product Description

ARACO PRIME SB is a two component high performance solvent based double coats application epoxy primer.

ARACO PRIME SB is commonly utilized as a part of a complete floor system. Once cured, **ARACO PRIME SB** has excellent abrasion and chemical resistance.

ARACO PRIME SB provides an attractive hard wearing and easily cleanable floor finish.

Standards Compliance

- BS EN 486:2009

Uses

ARACO PRIMER SB can be used:

- For floor coating for a variety of industrial application: assembly areas, parking floors, kitchens, showrooms, laboratories
- As a primer for **ARACO SB30**

Advantages

- Chemical Resistance
- Self-leveling
- High abrasion Resistance
- Hygienic, easy to clean
- Slip resistance finishing
- High adhesion to the substrate

Characteristics

Appearance	A: Resin B: Hardener
Mixed Density	1.1 kg/liter
Applicable humidity	75%
Recommended DFT	150 microns
Thin film dry time	About 9 hours
Max Recoat time	60 Hours
Pot Life	45 min
Setting time	3 – 5 Hours
VOC	<10 g/ltr
Storage Condition	Store in a dry shaded area at temperature between 5°C and 35°C.
Shelf life	Original Sealed container has a shelf life of 6 months if stored in the right conditions

ARACO PLAST FIBER

PACKAGE	5 liter and 20 liter kit
CONSUMPTION	0.1 L/m ² /2 coats

Surface Preparation

Substrate must be clean and free from all foreign or contaminating materials that might impair the quality of bond with the substrate such as oils, grease, curing compounds, dust, and loose aggregate or sand particles.

New concrete floors shall be at least 28 days old within moisture content of at less 5%

Mixing

Each of the component of **ARACO PRIME SB** should be individually stirred well before mixing them together.

Mix the materials using an electric drill with low rotation speed (300 rpm) for 2-3 minutes homogeneous mixture is obtained.

Manual mixing is allowed for small batch quantities for approx.1-2 min or until a lump free homogeneous mixture is obtained.

Application

The application of **ARACO PRIME SB** is best carried out when the surface to be coated is above 10°C and when humidity does not exceed 85 %.

ARACO PRIME SB is applied by a brush , roller, spike roller or by using a suitable serrated squeegee and then back rolled as long as the appropriate recommended thickness are maintained.

ARACO FOR ADMIXTURES & CONSTRUCTION MATERIALS S.a.I.

Lebanon, Beirut: Fax: +961 8 512413/ Tel:+961 1 562510

Email: aacm@araco-group.net / MOB:+961 3 104539



ARACO PRIME SB

Solvent Based High Performance Epoxy Primer

TECHNICAL DATA

Compressive Strength	Results	STANDARD
Average strength at 3 day	40 Mpa	
Average strength at 7 days	65 Mpa	ASTM C579
Average strength at 28 days	98 Mpa	
Bending Strength		
Average strength at 28 day	56 Mpa	ASTM D790
Tensile Strength		
Average strength at 28 days	42 Mpa	ASTM C307
Bond Strength		
Average Strength at 28 days	10 Mpa	ASTM D4541
Water Absorption		
Max water absorption	0.004	ASTM D413

Safety instructions

Product may cause skin irritation. Wear gloves and goggles and apply barrier cream to hands. In contact with eyes or mucous membrane, flush immediately with plenty of warm water and seek medical attention without delay.

Legal notes

The information, recommendations and application - based on ARACO current knowledge and experience of the products when properly stored, handled and applied under normal conditions. ARACO products are guaranteed against defective materials and manufacture and are sold subject to its standard conditions. Users should always refer to the most recent Technical Data Sheet for the product concerned, copies of which will be supplied on request.

ARACO FOR ADMIXTURES & CONSTRUCTION MATERIALS S.a.l.

Lebanon, Beirut: Fax: +961 8 512413/ Tel:+961 1 562510

Email: aacm@araco-group.net / MOB:+961 3 104539